

Evaluating the cytotoxic potential of biocompatible superparamagnetic iron oxide nanoparticles as platinum based-drugs nanocarriers


Gustavo B. da Silva^{1,2*}, Rocío Costo², José M. Rojas³, Domingo F. Barber³, M. Puerto Morales², Carlos J. Serna², Maria D. Vargas¹, Célia M. Ronconi¹

¹ Instituto de Química, Universidade Federal Fluminense, Niterói-RJ, Brazil, ² Departamento de Inmunología y Oncología, Centro Nacional de Biotecnología (CNB)/CSIC, Madrid, Spain,

³ Departamento de Biomateriales y Materiales Bioinspirados, Instituto de Ciencia de Materiales (ICMM/CSIC), Madrid, Spain.

*e-mail: gustavobezerrads@gmail.com

Superparamagnetic iron oxide nanoparticles (SPIONs) have become one of the most promising nanosystems for drug delivery. Thus, this work describes the synthesis of 13 nm SPIONs (**M13**) using a coprecipitation method, followed by acid treatment aiming to improve the colloidal properties. Functionalization with citric acid (CA) and amino-modified dextran (Dex-NH₂) afforded the nanosystems **M13@CA** and **M13@CA@Dex**, respectively, with good aqueous stability. The Dex-NH₂ was further modified with platinum(II) complexes and attached onto SPIONs, affording the superparamagnetic nanosystems **M13@CA@DexPt1-2** (DexPt1 = [Pt(Dex-NH₂)Cl₃] and DexPt2 = [Pt(NH₃)₂(Dex-NH₂)(H₂O)]). They exhibited excellent aqueous colloidal stability where the hydrodynamic diameters (D_H) were kept below 150 nm over a large range of pH (2.0-12.0) and were unaffected by PBS addition. Cytotoxicity assays of the nanosystems were evaluated in Pan02 (pancreatic ductal adenocarcinoma) and MDA-MB-231 (human breast) cell lines. **M13@CA@DexPt1-2** and cisplatin (control) showed poor cytotoxicity in Pan02. However, all nanosystems were internalized. Interestingly, magnetic hyperthermia measurements were carried out in Pan02 cells and enhancement in the cytotoxicity of **M13@CA@DexPt1-2** was observed.



Scheme 1. Synthesis of dextran-coated SPIONs functionalized with platinum complexes.

Demirer, G. S.; Okur, A. C.; Kizilel, S.; *J. Mater. Chem. B* **2015**, 3, 7831. Gutiérrez, L.; Romero, S.; da Silva, G. B.; Costo, R.; Vargas, M. D.; Ronconi, C. M.; Serna, C. J.; Veintemillas-Verdaguer, S.; Morales, M. P.; *Biomed. Eng.-Biomed. Tech.* **2015**, 60, 417.

CAPES, CNPq (550572-2012-0 and 279444/2013-9), NANOMAG (EC FP-7 604448)